





| Backing: | 2.0 mil Aluminum Foil | | |
|-----------------|--------------------------------|------------------------|--|
| Adhesive: | Synthetic Rubber | | |
| Liner: | Unbleached Natural Kraft Paper | | |
| Colors: | Aluminum | | |
| Specifications: | | UL 723 Classified | |
| Standard Sizes: | | 48mm x 46M, 72mm x 46M | |

Applications

 Taping joints and seams in duct work for A/C, heating, and ventilation systems

- General purpose industrial and automotive uses
- Insulation seaming and patching

| Features | Benefits |
|-------------------------------|--|
| 2.0 mil Aluminum Foil Backing | Conformable to fit corners and joints |
| | UV and moisture resistant |
| | Mold and mildew resistant |
| Synthetic Rubber Adhesive | Non-solvent for less odor and low VOC content |
| | Extreme high tack, aggressive bond to surfaces |
| | Good all-weather performance |
| UL 723 Classified | Meets flammability requirements for use in |
| | construction and marine applications |
| Low VOC Content | Can contribute toward satisfying EQ Credit 4.1 |
| | (Low Emitting Materials) under LEED® |

| Typical Test Va | lues |
|------------------------|------|
|------------------------|------|

| Standard UOM | Metric UOM | Test Method |
|--------------|---|--|
| 5.0 mils | 0.127 mm | ASTM D-1000 |
| 2.0 mils | 0.051 mm | ASTM D-1000 |
| 130 oz/in | 14.22 N/cm | PSTC-101 |
| 15 lb/in | 26.27 N/cm | ASTM D-1000 |
| 40 to 200 °F | 4 to 93 °C | |
| 15 | | |
| 10 | | |
| <1 g/L | | |
| | Standard UOM 5.0 mils 2.0 mils 130 oz/in 15 lb/in 40 to 200 °F 15 10 10 | Standard UOM Metric UOM 5.0 mils 0.127 mm 2.0 mils 0.051 mm 130 oz/in 14.22 N/cm 15 lb/in 26.27 N/cm 40 to 200 °F 4 to 93 °C 15 10 10 10 |

Recommended Storage Conditions: 60-80 °F at 40-60% RH Standard Shelf Life (at 25C): 36 months from date of manufacture.

The information presented herein was prepared at BERRY GLOBAL, INC. (25 Forge Parkway Franklin, MA 02038) by qualified technical personnel. To Berry's knowledge it is true and accurate. However, the information and recommendations are furnished for these products with the understanding that the purchaser or user, as the case may be, will independently determine that the product is suitable for the intended use, and that such use complies with all applicable federal, state and local laws and regulations. The data are typical values submitted only for the user's information and consideration, and do not constitute a warranty of any kind (including but not limited to a warranty of merchantability or of fitness for a particular purpose), or a representation for which BERRY assumes any legal responsibility.

