

# ALF150L

## UTILITY ALUMINUM FOIL TAPE WITH LINER

### DESCRIPTION

A general purpose aluminum foil tape with high tack pressure-sensitive rubber based adhesive. For seaming and sealing fiberglass duct board and duct wrap to enhance appearance and maintain vapor barrier integrity. Recommended minimum application temperature 40°F (4°C). The shiny aluminum backing offers excellent reflective properties (i.e. heat, light). White SCK liner.

### PRODUCT APPLICATIONS

HVAC (Heating, Ventilation and Air Conditioning) applications. For use also in Industrial, Appliance, Marine and Aerospace industries.

*\*\* Tape is best applied using plastic squeegee (99982)*

### GOVERNMENT COMPLIANCE

Test in accordance with ASTM E-84 / UL-723



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
Customer Service: 800.IPG.8273 | 800.474.8273  
Tape Technical Service: 877.447.4832  
www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 06/20

# INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

<b>Backing</b>	1.6 mil (40μ) Aluminum Foil
<b>Adhesive</b>	Synthetic Rubber / Resin
<b>Tensile Strength</b> (lbs./in width) ASTM D-3759	20 (87.5 N/25mm)
<b>Elongation</b> (% at break) ASTM D-3759	3
<b>Adhesion to Steel</b> (oz./in. width) ASTM D-3330	95 (26 N/25mm)
<b>Total Thickness w/o liner</b> (mil) ASTM D-3652	3.4 (0.086 mm)
<b>Flame Spread</b> ASTM E-84 / UL-723	≤ 25
<b>Smoke Developed</b> ASTM E-84 / UL-723	≤ 50
<b>Operating Temperature Range</b>	0°F ~ +225°F -18°C ~ +107°C

