### **PT 7** 14 DAY UV-RESISTANT SPECIALTY PAINTERS MASKING TAPE

#### DESCRIPTION

Conformable crepe paper masking tape with acrylic adhesive. Secure adhesion and clean removal from most surfaces. Resistant to U.V. (up to 14 days), humidity and paint bleed-through.

#### **PRODUCT APPLICATION**

For interior masking wherever tape (adhesive) will be exposed to sunlight. Compatible with polyurethane coated surfaces, wall-paper, new, or freshly painted wallboard.

#### NOTE

Not recommended for use on lacquer coated surfaces or un-finished wood.

# ipg

100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA Customer Service: 800.IPG.8273 | 800.474.8273

intertape polymer group™

Tape Technical Service: 877.447.4832

. www.itape.com | info@itape.com

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 5/13

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

#### **NOMINAL VALUES**

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

Backing	Coarse Crepe Paper
Adhesive	Acrylic
<b>Tensile Strength</b> (Ibs/in) ASTM D3759	22 (96 N/25mm)
<b>Elongation</b> (% at break) ASTM D3759	8
<b>Adhesion to Steel</b> (oz/in) ASTM D3330	18 (4.9 N/25mm)
<b>Total Thickness</b> (mil) ASTM D3652	5.8 (0.147mm)
Temperature Resistance	40°F to 120°F (4.4°C to 49°C)
Color	Dark Blue



