

# SG/519

## MEDIUM GRADE PAPER MASKING TAPE

### DESCRIPTION

A beige, conformable, semi-bleached crepe paper masking tape coated with pressure-sensitive natural rubber adhesive. Capable of withstanding bake temperatures up to 180°F (82°C) for up to one hour and/or exposure to ultra-violet (UV) light for up to five hours. Offers consistent conformability and tensile strength for general purpose bundling, protecting, and various industrial applications.

### PRODUCT APPLICATION

Interior paint masking, spray painting (air-dry) autos, boats, etc., boat manufacturing (fiberglass), silk screening, mail rooms, marble manufacturing (man-made), golf club shaft (build-up), carpet pad / pad splicing, freezer tape, and light bundling, packaging, splicing and tabbing.

### GOVERNMENT COMPLIANCE

PPP-T-42C, Type I  
UU-T-106, Type I  
C.I.D. A-A-883, Type I



100 Paramount Drive, Suite 300 | Sarasota, FL 34232 | USA  
Customer Service: 800.IPG.8273 | 800.474.8273  
Tape Technical Service: 877.447.4832  
[www.itape.com](http://www.itape.com) | [info@itape.com](mailto:info@itape.com)

While we believe them to be reliable, the statements and information herein are only for general guidance and are not warrants or guarantees for accuracy and completeness. The user must, by test or otherwise, determine suitability for this purpose. There is no warranty of fitness for a particular purpose. Our standard term and conditions of sale apply exclusively to all orders, and all liability for damages of any kind, including consequential, exceeding purchase price is excluded. No one is authorized by us to make oral warranties. We reserve the right to make changes without notice or obligation in our products and publications.

EFFECTIVE: 09/20

## INTERTAPE POLYMER GROUP® TECHNICAL DATA SHEET

### NOMINAL VALUES

The following data are nominal values based on PSTC, ASTM and other standard tests. The data should not be considered as specifications.

<b>Backing</b>	Crepe Paper
<b>Adhesive</b>	Natural/Synthetic Rubber
<b>Adhesion to Steel</b> (oz/in of width) PSTC-101	31 (8.5 N/25mm)
<b>Tensile Strength</b> (lbs/in of width) PSTC-131	20 (87.8 N/25mm)
<b>Elongation</b> (% at break) PSTC-131	12
<b>Total Thickness</b> (mils) PSTC-133	6.0 (0.15mm)
<b>Quick Stick to Steel</b> (oz/in of width) PSTC-5	14 (3.8 N/25mm)
<b>Color</b>	Beige

