

PC 599

Shurtape®
TRUE TO YOUR WORK™

SHURGRIP® HEAVY DUTY CO-EXTRUDED DUCT TAPE

TYPICAL APPLICATIONS

- For heavy duty sealing, seaming, repairing, holding and waterproofing applications that require aggressive stick and superior hold
- Also used in the remediation and restoration industries
- For temporary or permanent use

PRODUCT FEATURES

- Aggressive adhesion
- All-weather durability
- Improved holding power to poly-sheeting and steel
- Consistent, low-force unwind off the roll
- Hand-tearable in cross and machine directions
- Waterproof backing
- Green Point Contributor product
- Made using Polybonded CO-EX Technology®

CONSTRUCTION

Overall Grade/Function: Heavy Duty
Backing: Polyethylene film with a cloth carrier
Adhesive: Natural rubber

STANDARD WIDTH(S)

48 mm 72 mm

STANDARD LENGTH(S)

55 m

Contact your Shurtape sales representative for other available sizes


STORAGE AND USAGE CONDITIONS

Tape should be stored in its original packaging in a cool, dry area away from direct sunlight and should be used within 12 months of date of shipment. Surfaces to which tape is applied should be clean, dry and free of grease, oil or other contaminants.

COLOR(S)



SILVER
(SIL)



WHITE
(WHI)



RED
(RED)



BLACK
(BLK)

PHYSICAL PROPERTIES STANDARD METRIC

Tensile Strength	20 lbs/in width	35.0 N/10 mm
Adhesion to Stainless Steel	131 oz/in width	14.34 N/10 mm
Thickness	9 mils	0.23 mm
Elongation	21%	21%
Service Temperature Range	40 F to 200 F	4 C to 93 C

Physical and performance characteristics shown above are obtained from tests recommended by PSTC, ASTM, government agencies or Shurtape Technologies, LLC, Quality Assurance and Technical Service Departments and do not represent a guarantee of product performance. Individual rolls may vary slightly from these averages. The user should determine whether the product is fit for a particular purpose and is suitable for the user's method of application before use.

APPLICABLE STANDARDS

US Green Building Council – LEED® Point Contributor Product;
UL 723, FSI 0/SDI 0

